

CON ADD Gold 102 S

High range water reducing & super plasticizing admixture with strong slump retainer.



DESCRIPTION:

CON ADD Gold 102 S is a high range of water-reducing & super plasticizing admixture for Concrete & Mortar based on polycarboxylic polymers with long chains designed to enable the water content of the concrete to perform more effectively.

This effect can be used in high strength, low W/C ratio, and flowable concrete mixes, to achieve the highest durability and performance in the ready-mix and precast concrete industries. It also provides a long-time slump retainer product.

TYPICAL USES:

CON ADD Gold 102 S is suitable for the applications:

- High strength and high-performance concrete (HPC).
- Self-compacting concrete and flowing concrete.
- High levels concrete pumping.
- High durability concrete reducing concrete permeability.
- Structures with congested reinforcement.

ADVANTAGES:

- High water reduction, resulting in higher density, higher strength, and reduced permeability.
- Easier and faster pumping of concrete.
- Increased workability.
- Increased concrete durability and uniformity.
- Reduced shrinkage and cracking.
- Reduced rate of carbonation of the concrete.
- Optimizes cement utilization.
- Improves shrinkage and creep behaviors.
- Impermeable concrete through very high water reduction.
- Minimizes segregation and bleeding problems by improving cohesion.
- Increased workability levels are maintained for a longer time.
- Chloride-free, safe for use in prestressed and reinforced concrete.

TECHNICAL SPECIFICATIONS:

Composition :	A mix of a few types of modified polycarboxylates. polymer.
Appearance :	Light brownish liquid
PH :	7.4
Specific gravity :	1.055 ± (0.02) g/cm ³
CL :	Nil
Density :	1.031 g/cm ³
Density of water :	1.031 g/cm ³
Sold contain :	36.05 %

STANDARD:

CON ADD Gold 102 S
complies with BS EN934-2:1998
and ASTM C494, Type G.

APPLICATION:

Recommended dosage: (0.5 % - 1.5 %) by weight of total cementitious materials.

IMPRTANT GUIDANCE:

- The standard rules of good concreting practice, concerning production and placing, are to be followed.
- Laboratory trials shall be carried out before use on a large scale, especially when using a new mix design or producing new concrete components.
- Fresh concrete must be cured properly and the standard curing method applied, as early as possible.
- A suitable mix design has to be taken into account.
- Do not use naphthalene-based admixtures with **CON ADD Gold 102 S**
- Overdosage with excess water will cause the following: high air entrainment, bleeding, segregation, and longer initial & final setting time.

PACKAGING & STORAGE:

- **Packing:** 1000 Liter IBC.
20Kg Pail.
- **Storage:** Store under cover, out of direct sunlight and protect from extreme temperatures.
- **Shelf life:** Shelf life is up to 12 months when stored as per recommendations.

HEALTH & SAFETY:

The information, and the recommendations relating to the application and end-use of Con Techproducts, are given in good faith based on our current knowledge and experience of the products when properly stored, handled, and applied under normal conditions by the given recommendation. We reserve the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned copies, which will be supplied on request.

As with all construction chemical products, caution should always be exercised. Protective clothing such as gloves and goggles should be worn. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally allowed, do not induce vomiting, but call for medical assistance directly.

Before each use of any product of CONTECH, its subsidiaries, or affiliates ("ConTech"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Datasheet which are available at www.concrete-tec.com Nothing contained in any CONTECH literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each CONTECH product as outlined in the current product label, Product Data Sheet before use of the CONTECH product. CONTECH warrants this product for one year from the application date to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. The user determines the suitability of the product for the intended use and assumes all risks. The user's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

Contech endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the Technical Data Sheets specifications upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements.